

# Antek

## MADISON

### Plastics Corporation

### Polypropylene Copolymer - 35MFR

PHYSICAL PROPERTIES	ASTM METHOD	VALUES
Melt Flow (Condition) (g/10 min)	D1238	<b>35.00 (230/2.16)</b>
Tensile Strength @ Yield (PSI)	D638	<b>3.74x10<sup>3</sup></b>
Density(g/cm <sup>3</sup> )	D1505	<b>0.9</b>
Elongation @ Yield (%)	D638	<b>11</b>
Flexural Modulus (PSI)	D790	<b>1.76x10<sup>5</sup></b>
Notched Izod (ft-lb/in)	D256	<b>2.1</b>
Gardner Impact (in-lbs)	D3029	<b>24</b>
<b>FEATURES:</b>		
High stiffness, melt flow, impact, process & excellent mold release		
<b>Processing Method: Injection</b>		

#### TORONTO

Antek Madison Plastics  
100 Finchdene Square  
Scarborough, ON  
M1X 1C1

Phone: (416)-321-1170  
Fax: (416)-321-2809

#### CHICAGO

Antek Madison U.S.A  
8822 South Dobson Avenue  
Chicago, IL  
60619

Phone: (773) 933-0900  
Fax: (773) 933-1250