



Antek Madison Plastics Corp
100 Finchdene Sq.
Scarborough, Ontario M1X 1C1
Phone: (416) 321-1170
Fax: (416) 321-2809

12% Glass Fiber Reinforced, Chemically Coupled, Polypropylene, Black

PROPERTIES	TEST METHOD	VALUES	UNITS
PHYSICAL			
Melt Flow Rate, 230 °C/2160g	ASTM D1238	8	g/10min
Reinforcement Content	ASTM D2584	12	%
Specific Gravity	ASTM D792	0.99	
MECHANICAL			
Tensile Strength	ASTM D638	8,800	psi
Flexural Modulus	ASTM D790	420,000	psi
Izod Impact - Notched at 23 °C	ASTM D256	0.9	ft-lb/in
THERMAL			
Heat Deflection Temperature at 264 psi	ASTM D648	275	°F

Sincerely,

Antek Madison Plastics
Quality Control