



Antek Madison Plastics Corp
100 Finchdene Sq.
Scarborough, Ontario M1X 1C1

February 28, 2023

Phone: (416) 321-1170
Fax: (416) 321-2809

TECHNICAL DATA SHEET
PAGE 1 OF 1

MATERIAL: Polypropylene copolymer, 20% GF, chemically coupled black pellets

TYPICAL PROPERTIES	NOMINAL VALUE English Units	TEST METHOD
PHYSICAL		
Melt Flow Rate (190°C/2.16 kg)	8 g/10 min	ASTM D1238
Specific Gravity	1.05	ASTM D792
Reinforcement Content	20%	ASTM D2584
MECHANICAL		
Tensile Strength	7500 psi	ASTM D638
Notched Izod Impact	2.5 ft-lb/in	ASTM D256
Flexural Modulus	480,000 psi	ASTM D790
THERMAL		
Heat Deflection Temperature @ 264 psi	274	ASTM D648

Sincerely,

Antek Madison Plastics Corp.
Quality Control

Antek Madison Plastics Corp has no control over the use to which others may put this material; it does not guarantee that the same results as those described will be obtained. Antek Madison Plastics Corp does not guarantee the effectiveness or safety of any material for the design as well as the suitability of the material or designs of both for his own particular use. Statements concerning possible or suggested uses of the materials of design described herein are not to be constructed as recommendations for use of such materials or designs