



Antek Madison Plastics Corp
100 Finchdene Sq
Scarborough, Ontario M1X 1C1
Phone: (416) 321-1170
Fax: (416) 321-2809

04-03-23

TECHNICAL DATA SHEET

PET .80IV CLR VIRGIN FDA PELLETS

| Property | Test Method | English | SI |
|----------------|---------------|---------|-------------|
| I.V. | ASTM D5225 | dl/g | 0.80 ± 0.02 |
| AA Content | WN-B010-9013E | *mg/kg | -1.0 ± 1.0 |
| Color-B | WN-B010-7136E | *mg/kg | ≤1.0 |
| Color-L | WN-B010-7136E | *mg/kg | ≥55 |
| *COOH Content | WN-B010-7013E | mol/t | ≤30 |
| *Melting Point | WN-B010-7089E | °C | 77± |
| Powder | GB17931-2003 | *mg/kg | ≤80 |
| Moisture | GB17931-2003 | *wt.% | ≤0.3 |

Data Properties Disclaimer: Antek Madison Plastics Corp shall not be responsible for the applicability, or the accuracy of the information contained herein, or the suitability of the products described herein for any particular purpose. It is the ultimate responsibility of the user to ensure that the product is suited, and the information is applicable to the user's specific application. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made with respect to the products described herein or with respect to the use of the products described herein.

Antek Madison Plastics Corp.

Laboratory Department