



Antek Madison Plastics Corp
100 Finchdene Sq
Scarborough, Ontario M1X 1C1
Phone: (416) 321-1170
Fax: (416) 321-2809

Technical Data Sheet

PET .84IV CLR VIRGIN FDA PELLETS

Property	Test Method	English	SI
I.V.	ASTM D5225	dl/g	0.84
AA Content	WN-B010-9013E	*mg/kg	<1.0
Color-B	WN-B010-7136E	*mg/kg	<1.0
Color-L	WN-B010-7136E	*mg/kg	>80.0
*COOH Content	WN-B010-7013E	mol/t	<35
*Melting Point	WN-B010-7089E	°C	>240
Dust	GB17931-2003	*mg/kg	<100
Moisture	GB17931-2003	*wt.%	<0.2

Data Properties Disclaimer: Antek Madison Plastics Corp shall not be responsible for the applicability, or the accuracy of the information contained herein, or the suitability of the products described herein for any particular purpose. It is the ultimate responsibility of the user to ensure that the product is suited, and the information is applicable to the user's specific application. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made with respect to the products described herein or with respect to the use of the products described herein.

Antek Madison Plastics Corp.

Laboratory Department